

GRABO

1905

TERRANA ECO

Technical datasheet

Residential

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	2,6
Wear layer thickness	EN ISO 24340	mm	0,15
Width of roll	EN ISO 24341	m	2 / 2,5 / 3 / 3,5 / 4
Length of roll	EN ISO 24341	lm	18-27
Total weight	EN ISO 23997	kg/m2	1,5
CLASSIFICATION			
European classification	MSZ EN 26986	class	21
PERFORMANCE			
Abrasion group	a priori EN 651	class	T
Residual indentation	EN ISO 24343	max. mm	0,35
Dimensional stability	EN ISO 23999	max. %	0,2
Impact sound reduction	TD 99030-01 §1.2	DLw (dB)	16
Slip resistance	EN 13893	class	DS
Chemical resistance	EN ISO 26987		✓
Light fastness	EN ISO 105-B02 3. method	grade	6
Castor chair resistance	EN 425		✓
Seaming method			heat or cold weld
Warranty		year	5
CE MARKING	EN 14041		✓

GRABOPLAST Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
info@grabo1905.com www.grabo1905.com